

RUBBER-SEAL®

Medallion™

Refinish System

STOP RUST IN ITS TRACKS!

RUST PREVENTIVE COATING is a high solids, 1K, underbody coating formulated to permanently stop corrosion. It protects a variety of substrates from water, chemicals, salt and other corrosive contaminants. **MRS-370/370G** dries to a flexible, rock-hard finish that will not crack, chip, flake or peel. It is V.O.C. compliant in North America and available in **Gloss Black (MRS-370)** and **Gloss Grey (MRS-370G)**.

- ◆ Seals & protects surfaces from harsh contaminants
- ◆ Dries to a flexible, rock-hard, non-porous finish
- ◆ Will not crack, chip, flake or peel
- ◆ Ideal for use on any surface exposed to extreme conditions
- ◆ Can be topcoated for added UV protection



RUBBER-SEAL®

Medallion™

Refinish System

RUST PREVENTIVE COATING

SUITABLE SUBSTRATES

Cold Rolled Steel*

Stainless Steel* Galvanized/Galvaneal*

Aluminum*

Factory E-coats*

2K Epoxy Primer

2K Urethane Primer

*Properly cleaned and sanded

MIXING

Ready-to-Spray (Optional: Reduce up to 10% with Zero VOC Reducer)

NOTE: DO NOT SHAKE, STIR THOROUGHLY BEFORE USE. Do not return unused product back to can after use. BEFORE CLOSING CONTAINER, APPLY A SHEET OF PLASTIC WRAP OVER THE CAN AND ATTACH LID. COATING WILL ADHERE LID TO CAN IF PLASTIC WRAP IS NOT APPLIED.

APPLICATION

SPRAY: Apply 2-4 medium wet coats, while maintaining a gun distance of 12-14 inches. Allow 3 to 8 hours between coats depending on temperature and humidity. Each coat should be dry to touch with no tackiness before applying next coat.

ROLL-ON: Apply thin, even coats using a nylon brush until desired coverage is achieved. Allow 3 to 8 hours between coats depending on temperature and humidity. Each coat should be dry to touch with no tackiness before applying next coat.

NOTE: Rust Preventive Coating should not be applied when temperatures are below (50°F/10°C). The coating will have a tendency to bubble while curing when applied to heavily.

SURFACE PREPARATION

Remove loose rust or scale by using a stiff wire brush or grinder. Thoroughly clean the surface with a quality Wax & Grease Remover. If the surface is bare, smooth metal it is recommended to sand with 36-80 grit sandpaper or sandblast the surface to a medium profile for optimum adhesion. Pre-painted surfaces can be sanded with 120-180 grit sandpaper to remove gloss.

DRY TIMES (Air Dry @ 77°F & 50% Relative Humidity)

To Recoat 3 – 8 hours depending on temperature & humidity

To Topcoat 3 – 8 hours depending on temperature & humidity (After 24 hours, sand with 400 grit)

For more information regarding the use of this product review the TDS & SDS at medallionrefinish.com .

Part No.	Description	Units/Case
MRS-370	Gloss Black Rust Preventive Coating, Gallon	4
MRS-370-Q	Gloss Black Rust Preventive Coating, Quart	4
MRS-370G	Gloss Grey Rust Preventive Coating, Gallon	4
MRS-370G-Q	Gloss Grey Rust Preventive Coating, Quart	4

Rubber-Seal® Medallion™ Refinish System

5751 N. Webster St. • Dayton, OH • 45414

1.800.257.6547 • Fax 1.937.890.6320

medallionrefinish.com

LIT-038