

www.medallionrefinish.com

5751 N. Webster Street Dayton, OH 45414-0802 Phone 937-890-6547 Toll Free 800-257-6547 Fax 937-890-6320

## MRS-774

# TECHNICAL DATA

## 1K Acrylic Sealer

#### **DESCRIPTION:**

MRS-774 1K Acrylic Sealer is a super smooth, one component primer sealer. It can be used on all previously coated metal surfaces to provide a uniform surface prior to topcoat. MRS-774 1K Acrylic Sealer has tremendous adhesion and excellent color holdout. Ready to spray; no mixing required. Pour unused sealer back in the can for future use.

#### **FEATURES:**

- ✓ Superior adhesion
- ✓ Excellent color hold-out
- ✓ Provides an extremely smooth surface
- ✓ Use "wet-on-wet"; no sanding required before topcoating.
- ✓ Medium gray for ease of coverage
- ✓ Can be used on small bare steel cut-through spots





#### **INSTRUCTIONS:**

Mix MRS-774 1K Acrylic Sealer thoroughly before each use. If using on a mixing machine, mix 2-3 minutes. Do not leave this primer on a mixing bank.

#### **GUN SETUP:**

Conventional Gravity	1.3mm -1.4mm	40-45 psi @ gun
Siphon	1.3mm -1.4mm	40-45 psi @ gun
HVLP gravity	1.3mm -1.4mm	8-10 psi @ gun



#### MIXING:

MRS-774 1K Acrylic Sealer is ready to spray. No activator is required.



#### TINTING:

It is not recommended to tint MRS-774 1K Acrylic Sealer.



#### SURFACE PREPARATION:

Wash area with soap and warm water. Thoroughly clean area with RS-608 Slow Wax and Grease Remover or RS-609 Wax and Grease Remover. RS-611 or RS-612 can be used where VOC restrictions apply.



#### APPLICATION:

Apply 1 uniform coat using a good quality spray gun with a 1.3mm-1.4mm fluid tip. Allow 15 minutes before topcoating. After overnight dry, clean, scuff and recoat before applying basecoat.



www.medallionrefinish.com

5751 N. Webster Street Dayton, OH 45414-0802 Phone 937-890-6547 Toll Free 800-257-6547 Fax 937-890-6320

### **TECHNICAL DATA**

Color	Medium Gray	
Activator/Hardener	Not required	
Reducer	Not required	
Mix Ratio	Ready to use	
Pot Life	N/A	
Number of Coats	1	
Flash Time before topcoating	15 minutes@75°F (23.9°C)	
Recoat w/o sanding	N/A	
Dry to Sand	N/A	
Air Dry 70°F (21°C) 50% RH	N/A	
Force Dry	N/A	
Gun Set-Up Gravity Feed (HVLP)	1.3mm – 1.4mm	
Air Pressure @ Gun HVLP	8 – 10 psi	
Air Pressure @ Gun conventional	40 -45 psi	
V.O.C. Limit Regulatory Actual	4.6 lbs/gal (552 g/l) 4.6 lbs/gal (552 g/l) 3.78 lbs/gal. (393 g/l)	
Sprayable V.O.C.*	4.6 lbs/gal (552 g/l)	
% Solids Sprayable by Weight	31%	
Coverage Sq. Ft. / gal @ 1 mil*	481 sq/. ft.	
Destant	Quarts	
Package Number per case (quarts) Gallons	Gallons 6 4	
Shelf Life	12 months	





