



www.medallionrefinish.com

5751 N. Webster Street
Dayton, OH 45414-0802
Dayton 937-890-6547
Toll Free 800-257-6547
Fax 937-890-6320

MRT-684


TECHNICAL DATA

Basecoat White

DESCRIPTION:

MRT-684 Basecoat White is a direct replacement for PPG DMD 1684 White Base and Matrix MT-84 White Basecoat which is also used as the white tint for DBC and DBU basecoat systems. **MRT-684 Basecoat White** is available in quarts and gallons.

FEATURES:



INSTRUCTIONS:

Agitate thoroughly before use. Use according to paint manufacturers' mixing recommendations. Reseal after each use. **MRT-684 Basecoat White** should be placed on a mixing machine.



APPLICATION:

Apply product according to paint manufacturers' recommendations.



V.O.C.

Regulatory:
5.2 lbs/gal. (623 g/l)
Actual
5.2 lbs/gal (623 g/l)

MRT-684 Basecoat White reduces 1:1 (100%) with the RS-1800 series reducers.

RS-1860 Fast Urethane Reducer

RS-1870 Medium Urethane Reducer

RS-1885 Slow Urethane Reducer

RS-1895 X-Slow Urethane Reducer

Technical Data Information (Basecoat)

Flash Time between coats	5 minutes
Dust Free Time	5 minutes
Tack Free Time	5 minutes
Spray to coverage	2-3 coats
Dry to sand time (air dry)	10-15 minutes

MRT-684
7/09



5751 N. Webster Street
Dayton, OH 45414-0802
Dayton 937-890-6547
Toll Free 800-257-6547
Fax 937-890-6320

www.medallionrefinish.com

Time to recoat with basecoat	10-15 minutes
Time to topcoat with clearcoat	25-30 minutes
Gun Set-up	1.3mm-1.4mm fluid tip
Air Pressure @ Gun	40-45 psi

Part Numbers

MRT-684 Basecoat White-gallon 4 per case)
MRT-684-Q Basecoat White-quart (6 per case)

DISCLAIMER: PPG, Deltron and Concept are registered trade names of PPG. PPG does not manufacture, endorse or guarantee Rubber-Seal Products or Medallion™ Refinish System products.

DISCLAIMER: Matrix is a registered trade mark name of Matrix System Automotive Finishes. Matrix does not manufacture, endorse or guarantee Rubber-Seal Products or Medallion™ Refinish System products



MRT-684
7/09