www.medallionrefinish.com

5751 N. Webster Street
Dayton, OH 45414-0802
Dayton 937-890-6547
Toll Free 800-257-6547
Fax 937-890-6320

MRT-97 TECHNICAL DATA

Basecoat Jet Black

DESCRIPTION:

MRT-97 Basecoat Jet Black is a direct replacement for PPG DBC 9700. **MRT-97 Basecoat Jet Black** is available in an F-style gallon and a round quart.

Part Numbers

MRT-97	**Black Basecoat**-gallon 4 per case)
MRT-97-Q	**Black Basecoat**-quart (6 per case)

INSTRUCTIONS:

Shake can thoroughly before use. Mix **MRT-97 Basecoat Jet Black** with RS-1800 Series standard urethane grade reducer at a 1:1 mix ratio (100%). Stir thoroughly and pour through a strainer into the paint cup. Reseal after each use.

RS-1860 Fast Urethane Reducer
RS-1870 Medium Urethane Reducer
RS-1885 Slow Urethane Reducer
RS-1895 X-Slow Urethane Reducer

Note: For increased durability add 1-2 ozs. of MRS-122 Basecoat Activator per mixed sprayable quart of basecoat.

APPLICATION:

Apply 2-3 medium wet coats or until proper hiding is achieved. Allow 5-10 minutes flash time between coats.

Technical Data Information

V.O.C.

Regulatory:
5.41 lbs/gal. (648g/l)

Actual
5.41 lbs/gal. (648g/l)

5751 N. Webster Street
Dayton, OH 45414-0802
Dayton 937-890-6547
Toll Free 800-257-6547
Fax 937-890-6320

www.medallionrefinish.com

Flash Time between coats	5 minutes
Dust Free Time	5 minutes
Tack Free Time	10 minutes
Spray to coverage	2-3 coats
Coverage @ 1 mil	
Time to topcoat with clearcoat	25-30 minutes
Gun Set-up	
Gravity Fed	
1.3mm-1.4mm fluid tip	
Mini Jet	
1.2mm-1.4mm fluid tip	
Air Pressure @ Gun	40-45 psi

DISCLAMER: PPG, Deltron and Concept are registered trade names of PPG. PPG does not manufacture, endorse or guarantee Rubber-Seal Products or Medallion™ Refinish System products.

DISCLAIMER: Matrix is a registered trade mark name of Matrix System Automotive Finishes. Matrix does not manufacture, endorse or guarantee Rubber-Seal Products or Medallion™ Refinish System products