



www.medallionrefinish.com

5751 N. Webster Street
Dayton, OH 45414-0802
Toll-Free 937-890-6547
Phone 800-257-6547
Fax 937-890-6320

RS-592

TECHNICAL DATA

Rubber Coat

DESCRIPTION:

RS-592 is a modified asphalt undercoat designed for protection against corrosion. This material cures to a flexible coating contributing to sound deadening efficiency.



APPLICATION:

1. Shake well.
2. Use at room temperature, not under 50°F.
3. Spray thin, even coat over cleaned surface.
4. Short even strokes provide the best results.
5. Clean nozzle after use by turning can upside down and spraying.
6. Under normal circumstances, allow 4 hours before applying final finish.

TECHNICAL DATA:

Base	Asphalt
Color	Black
% Solids	75.0% ± 5.0%
Viscosity (Brookfield)	#6 @ 5 RPM – 40,000 ± 5,000
Weight/Gallon	10.79 lbs/gal.
Dry Time	Depending on temperature. 12-24 hours to optimum properties
Shelf Life	In unopened container, 1 year minimum.. Stirring may be required for return to original specs.
Flash Point	45°F
Salt Water Immersion	Excellent Resistance