

**PRODUCT DESCRIPTION**

**MRS-2720 Low VOC Blend Eze** is a blend of premium compliant solvents and resins designed to be used as a panel blender for 2K clearcoats and single-stage urethane paint systems. It is compatible with most single-stage urethane systems, basecoats and clearcoats. **MRS-2720** can also be used to check color match or layout of metallic colors. It is an excellent alternative to aerosol blending solvents in 2.1 VOC areas.

**SUITABLE SUBSTRATES**

All Medallion Clearcoat Systems	Acrylic Urethane Clearcoats
Activated Acrylic or Polyester Basecoats	Activated Single-Stage Urethanes

**MIXING****As a Panel Blender**

<b>1 part</b>	:	<b>1 part</b>
Activated Clearcoat	:	MRS-2720 Blend Eze
Activated Single-Stage Urethane		

**NOTE:** Make sure product is at room temperature (72°F) before mixing.

**As a Color Checker**

**RTS     MRS-2720**

**APPLICATION****As a Panel Blender**

Apply first coat of clearcoat or single-stage urethane over repair area  
 Apply the second coat of clearcoat or single-stage urethane past the edge of the first coat  
 Reduce the remaining mixed product 1:1 with MRS-2720  
 Apply the mixture over the edge with 50% overlap to melt in the blend edge  
 Straight MRS-2720 can be used to further melt-in the remaining blend edge  
 Recommended gun setup can be found on page 2 under Technical Data

**As a Color Checker**

Allow basecoat to dry according to paint manufacturer's recommendations  
 Apply 1-2 light coats of MRS-2720 Blend Eze over the basecoat blend area  
 Check for color match or metallic layout  
 Allow to dry 5-10 minutes before applying clearcoat

**PERSONAL PROTECTION**

- For use by trained professionals only
- Read label, directions and MSDS before use
- Wear appropriate Personal Protection Equipment (PPE) while mixing and spraying
- For additional health and safety information refer to the MSDS which can be found at [www.medallionrefinish.com](http://www.medallionrefinish.com)

---

## TECHNICAL DATA

Mix Ratio	1:1 or RTS
Gun Setup (HVLP)	1.2 mm – 1.4 mm
Air Pressure	8-10 psi HVLP 40-45 psi Conventional
Shelf Life (Unopened)	12 months

## HEALTH & SAFETY

See Material Safety Data Sheet and labels for additional safety information and handling instructions.

- The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels and MSDSs of all component, since the mixture will have the hazards of all its parts.
- Improper handling and use, for example, poor spray technique, inadequate engineering controls, and or lack of Personal Protective Equipment (PPE), may result in hazardous conditions or injury.
- Follow spray equipment manufacturer's instructions to prevent personal injury or fire.
- Provide adequate ventilation for health and fire hazard control.
- Follow company, product MSDS and respirator manufacturer's recommendations for selection and proper use of respiratory protection. Be sure employees are adequately trained on the safe use of respirators per company and regulatory requirements.
- Wear appropriate PPE such as eye and skin protection. In the event of injury, see first aid procedures on MSDS.
- Always observe all applicable precautions and follow good safety and hygiene practice.