

www.medallionrefinish.com

5751 N. Webster Street Dayton, OH 45414-0802 Phone 937-890-6547 Toll Free 800-257-6547 Fax 937-890-6320

# RS-224

# TECHNICAL DATA

### **Quick Cure Primerless Auto Glass Urethane**

#### **DESCRIPTION:**

**RS-224 Quick Cure Primerless Auto Glass Urethane** is a single-component medium viscosity windshield urethane for all factory urethane bonded auto glass. It is designed for full or close cutout windshield and backlite installations. This urethane is formulated for easy manual gun application and excellent shelf-life properties. Meets all factory specifications. A urethane compatible pinchweld primer must be applied to all bare metal areas of the pinchweld.

#### **FEATURES:**

- ✓ Low odor
- ✓ Excellent sag resistance
- Excellent flow viscosity at various temperatures
- ✓ Tack-free in one hour
- ✓ Excellent for water leak repair
- ✓ Excellent adhesion
- ✓ Meets FMVSS 212 & 216 strength requirements



#### **INSTRUCTIONS:**

Remove auto glass as recommended. Clean pinchweld of all sealants and contaminants. Surface to be bonded must be dry and free of all contaminants.

#### **APPLICATION:**

Apply **RS-225P Pinchweld Primer** to all bare metal areas and allow to dry. Install clean glass into opening using hand pressure to assure complete contact with adhesive.



#### **CLEAN-UP:**

RS-224 Quick Cure Primerless Auto Glass Urethane can be wiped off using a clean dry cloth and a wax & grease remover or general purpose solvent.



#### STORAGE:

RS-224 Quick Cure Primerless Auto Glass Urethane should be stored in a cool, dry area. To ensure maximum shelf life, store below 73°F (23°C) or refrigerate. It should not be exposed to conditions of elevated temperatures for long periods of time. Contents may prematurely age react if exposed to temperatures in excess of 120°F (49°C).



www.medallionrefinish.com

5751 N. Webster Street Dayton, OH 45414-0802 Phone 937-890-6547 Toll Free 800-257-6547 Fax 937-890-6320

## **TECHNICAL INFORMATIOIN**



Black
Slight
.41 lbs/gal (49 g/l)
277-230 g/min
<less 20%="" increase<="" td="" than=""></less>
900 psi minimum
400%
50-90 minutes
7 Days
12 months
10.5 Oz. Cartridge
12

Material Safety Data Sheet (MSDS) is available on our website www.rubber-seal.com

