

# BARRA CUDA HESION PROMOTER

Work smarter, not harder by using BARRACUDA Adhesion Promoter plus Sealer! This unique formula penetrates into the surface and bonds with multiple automotive substrates. BARRACUDA Adhesion Promoter plus Sealer also can act as a clear, non-sanding sealer in a variety of applications. It can be used on flexible and rigid plastics, fiberglass, and painted surfaces. BARRACUDA is compatible with all solvent based urethane, epoxy or acrylic lacquer primers, sealers and basecoats.







# LOW V.O.C. PLUS SEALER

- Excellent adhesion to multiple substrates
- Increased flexibility
- Fills sand scratches
- Reduces basecoat usage



RS-598

Contains: Net Wt. 15 oz. (425g)





- Excellent adhesion to multiple substrates
- Increased flexibility.
- Fills sand scratches
- Reduces basecoat usage





MRS-1250-0

Contains: 32 fl. oz. (946.35mL)

- Superior Adhesion
- Excellent Flexibility
- Fills Sand Scratches
- Reduces Basecoat Usage
- Works on Plastic, Fiberglass, Painted Metal & Aluminum
- Available in Quarts, Gallons & Aerosol

medallionrefinish.com



#### SUITABLE SUBSTRATES

Cured OEM Finishes

1K & 2K Primers

Fiberglass/SMC

Automotive Plastics

#### SURFACE PREPARATION

Clean all areas to be coated thoroughly with MRS-678 Scuff Paste and a Red Scuff Pad

Rinse thoroughly with clean water, do not allow MRS-678 to dry on the surface

Thoroughly dry the surface to be coated with clean compressed air (Surface must be completely dry)

#### MIXING

Ready to Spray

Stir MRS-1250 thoroughly before each use. If using RS-598 Barracuda Aerosol, then shake can 2 minutes before each use

#### DO NOT LEAVE MRS-1250 ON A MIXING BANK

## APPLICATION

Apply 1 uniform medium coat and allow 15 minutes before topcoating

If a 2nd coat is required, apply first coat in a light mist and atlow 3-5 minutes between coats

If allowed to dry for more than 24 hours, then clean, scuff and recoat with BARRACUDA Adhesion Promoter before topcoating

If applying basecoat over BARRACUDA Adhesion Promoter apply in light coats until uniform color is achieved

DO NOT apply heavy coats of basecoat over Barracuda Adhesion Promoter

### **AVAILABLE SIZES**

| Part No.   | Size           | Units/Case |
|------------|----------------|------------|
| MRS-1250   | Gallon         | 4          |
| MRS-1250-Q | Quart          | 12         |
| RS-598     | 15 oz. Aerosol | 12         |

#### **HEALTH & SAFETY**

See Safety Data Sheet, Technical Data Sheet and labels for additional safety information and handling instructions,

- . Before opening the packages, be sure you understand the warning messages on the labels and SDS
- . Improper handling and use, for example, poor spray technique, inadequate engineering controls, and or lack of Personal Protective Equipment (PPE), may result in hazardous conditions or injury.
- Follow spray equipment manufacturer's instructions to prevent personal Injury or fire.
- Provide adequate ventilation for health and fire hazard control.
- Follow company, product SDS and respirator manufacturer's recommendations for selection and proper use of respiratory protection. Be sure employees are adequately trained on the sale use of respirators per company and regulatory requirements.
- Wear appropriate PPE such as eye and skin protection. In the event of injury, see first aid procedures on SDS.
- Always observe all applicable precautions and follow good safety and hygiene practice.